

TECHNICAL DATA SHEET

FARBEX ALKALI RESISTING PRIMER

TDS: FBG1191 **FB/G119/1**

DESCRIPTION:

Farbex Alkali Resisting Primer is ideal as a high quality primer prior to painting. Resistant to solvents and salts.

RECOMMENDED USE:

Farbex Alkali Resisting Primer is ideal for use on walls and plaster.

AVAILABILITY:

1 litre, 2.5 litre, 5 litre

FINISH:

Matt

COLOUR:

White

TYPICAL S.G. (SPECIFIC GRAVITY):

1.10 @ 20 °C

VOLUME SOLIDS:

36%

WET FILM THICKNESS W.F.T

100 microns

DRY FILM THICKNESS D.F.T

35 to 40 microns

EXPECTED SPREADING RATE:

10 sq.m / litre

@ 40 microns D.F.T

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY:

4.0 Poise - C&P @ 25 °C

FLASH POINT:

Above 32 °C (closed cup)

DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 1 hour @ 20 °C

Hard dry: 4 hours @ 20 °C

Full hardness: 3 to 5 days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME:

Minimum 4 to 6 hours

APPLICATION SPECIAL CONDITIONS:

N/A

VOC CONTENT:

max 499 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Application N/A restrictions

Method: Brush or Roller

Thinner LO White (Max vol): Spirit(10%)

Nozzle size: 0.013"

Nozzle N/A

pressure:

Cleaning LO White Spirit

solvent:

Recoat Minimum 4 to 6

interval: hours

SURFACE PREPARATION:

Ensure all surfaces are clean, dry and free from grease, oil and any other contaminates. Use a Masonry Stabiliser on unstable brick, screed or plaster prior to painting. Existing painted surfaces should be cleaned, degreased and sanded to ensure an adequate "key" is produced. Remove all loose, flaking material and treat bare

For further advice contact Farbex Technical Services on 021 470 3596

The physical constants are subject to normal manufacturing tolerances.

Date printed 14 March 2024 Page 1 of 2

TECHNICAL DATA SHEET FARBEX ALKALI RESISTING PRIMER

TDS: FBG1191 **FB/G119/1**

areas as new substrate then prepare accordingly.

MIXING INSTRUCTIONS:

Mix well before use.

APPLICATION CONDITIONS:

As dictated by normal good painting practice. Care must be taken during application that the temperature is above the dew point to avoid any contamination. In confined spaces, provide adequate ventilation during application and drying.

PRECEDING COAT:

Apply Direct to stable surfaces (see Surface Prep section)

SUBSEQUENT COAT:

Suitable top coat.

REMARKS:

HEALTH AND SAFETY:

See safety data sheet - SDS 11325

ISSUED:

14 March 2024

REVISION:

3

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department on 021 470 3596.

For further advice contact Farbex Technical Services on 021 470 3596

The physical constants are subject to normal manufacturing tolerances.

Farbex Coatings
Unit 3, Centrepoint, Centre Park Road, Cork, Ireland
Tel.: 021 470 3596

Date printed 14 March 2024 Page 2 of 2