



Ralston Aqua All-Primer

High-quality, universal, water-dilutable adhesion primer on the basis of acrylate technology.



ralstoncolour.com/picto

- · Excellent adhesion
- Suitable in combination with all paint systems
- Excellent body
- · Recoatable in 4 hours
- · Extended wet edge time
- · Nice flow
- · Good coverage
- Easy application
- · Solvent free



PRODUCT

INTENDED USE Exterior and interior, as a primary and precoat resp. an adherent primer

for wood, aluminium, stony surfaces, synthetics (hard pvc) and

sendzimir galvanized steel. Can be applied over the existing traditional paintwork after first thoroughly cleaning and sanding the surface. As a

primary coat for the Ralston Aqua and Solvent paints.

SITUATION Exterior

Interior

PACKAGING 1 I, 2.5 I, 5 I

COLOURS All colours available via the Ralston AQ colour mixing system

GLOSS LEVEL Matt, approx. 10 G.U. at 60 °

BINDER Acrylate technology

PIGMENT High quality pigments and specific fillers

SOLIDS CONTENT Approx. 40 volume % VISCOSITY AT 20 °C Approx. 1,3 kg/dm3 VISCOSITY AT 20 °C Approx. 114 K.U.

DRYING TIME Drying time (20 °C / 65 % R.H.): dust-free after approx.0,5 hr;

recoatable after approx. 4 hr.

The stated drying times are typical and depend on such factors as

temperature and humidity.

ELASTICITY 6 mm Erichsen

NOTE: The properties and specifications can vary depending on the colour. The values stated are typical.

Product Data Sheet 2/6

Ralston Aqua All-Primer

APPLICATION

APPLICATION BY brush, roller, air spray

DILUTION Ready to use. If necessary max. 5 % water.

TOOLS/EQUIPMENT CLEANING Wate

APPLICATION TEMPERATURE / Min. 7 °C - max. 25 °C ambient and substrate temp., relative humidity

R.H. max. 85 %.

Substrate temperature min. 3 °C above dew point.

THEORETICAL COVERAGE 11,4 m2/l

FILM THICKNESS 35 microns dry film thickness (= approx. 88 microns wet film thickness)

Check the dew point regularly when applying at low temperatures. With wood and metal substrates, this can have a major influence on the ability to apply the coating, as well as on the drying and gloss of the

applied coating.

ENVIRONMENT AND CERTIFICATION

SAFETY INSTRUCTIONS The user is subject to the national legislation regarding safety, health

and environment. For more information and current data, see the latest

version of the Safety Data Sheet.

EU LIMIT VALUE VOC EU limit value for this product A/d: 130 g/l (2010). This product contains

a maximum of 130 g/l VOCs.

BREEAM We herewith conform that our product can be used in compliance with

BREEAM International New Construction. As per HEA 9, requirend evidence – completion phase: C 1.1 through to 1.8; in evidence of

compliance, the following must be submitted:

1. VOS (Volatile Organic Substance) content as determined by product

recipe.

2. Products grouped by category in accordance with European Decopaint Directive 2004/42/EC – Enclosure 2: Emission norm for

paints, lacquers and clear finishes, phase 2.

3. EU limit value for this product A/d: 130 g/l (2010). This product

contains a maximum of 130 g/l VOCs.

We apply the above harmonization procedure as recommended by the

Dutch Green Building Council.

BELGIAN EMISSION LABEL The product complies with the limit values and other stipulations of the

Royal Decree of 8 May 2014, which defines the threshold levels for emissions to the internal environment from construction products for designated, specific uses, as published in the Belgian Government

Gazette of 8 August 2014.

FRENCH EMISSION LABEL



Product Data Sheet 3/6

Ralston Aqua All-Primer

STORAGE AND USE PERIOD

STORAGE Cool and above freezing point; do not allow product quality to

deteriorate during storage.

USE WITHIN 12 Months (in unopened packaging)

After opening the packaging, the effect of 'preservatives' in the paint may be reduced. In exceptional cases, this can give bacteria and moulds free rein from outside, which could spoil the product.

Product Data Sheet 4/6

Ralston Aqua All-Primer

SYSTEM COMPOSITION - ADVICES

New, exterior, untreated, wood

- · clean / degrease and sand
- prime with Ralston Aqua All-Primer
- · pre-finish with Ralston Aqua All-Primer
- · finish with Ralston Aqua paints

New, interior, untreated, wood

- · clean / degrease and sand
- · prime with Ralston Agua All-Primer
- pre-finish with Ralston Agua All-Primer
- · finish with Ralston Agua paints

New, exterior, untreated, non-ferrous metal (galvanised steel, aluminium, copper)

- remove all traces of oxidation thoroughly, clean / degrease and sand
- prime with Ralston Aqua All-Primer
- pre-finish with Ralston Aqua All-Primer
- · finish with Ralston Aqua paints

New, interior, untreated, non-ferrous metal (galvanised steel, aluminium, copper)

- remove all traces of oxidation thoroughly, clean / degrease and sand
- prime with Ralston Aqua All-Primer
- · pre-finish with Ralston Aqua All-Primer
- finish with Ralston Aqua paints

New, exterior, untreated, plastics (hard PVC)

- · clean / degrease thoroughly, and sand
- prime with Ralston Aqua All-Primer
- · finish with Ralston Aqua paints

New, interior, untreated, plastics (hard PVC)

- · clean / degrease thoroughly, and sand
- prime with Ralston Aqua All-Primer
- · finish with Ralston Aqua paints

Existing, exterior, treated, wood

- · remove unsound paint coats
- clean / degrease and sand / rub down gloss thoroughly
- · prime bare patches with Ralston Aqua All-Primer
- pre-finish patches or entire surface with Ralston Aqua All-Primer
- · finish with Ralston Aqua paints

Existing, interior, treated, wood

- · remove unsound paint coats
- clean / degrease and sand / rub down gloss thoroughly
- prime bare patches with Ralston Aqua All-Primer
- pre-finish patches or entire surface with Ralston Aqua All-Primer
- · finish with Ralston Aqua paints

Existing, exterior, treated, non-ferrous metal (galvanised steel, aluminium, copper)

- remove unsound paint coats
- remove all traces of oxidation thoroughly, clean / degrease and sand
- · prime bare patches with Ralston Aqua All-Primer
- pre-finish patches or entire surface with Ralston Aqua All-Primer
- · finish with Ralston Aqua paints

Existing, interior, treated, non-ferrous metal (galvanised steel, aluminium, copper)

- · remove unsound paint coats
- remove all traces of oxidation thoroughly, clean / degrease and sand
- prime bare patches with Ralston Aqua All-Primer
- pre-finish patches or entire surface with Ralston Aqua
 All-Primer
- · finish with Ralston Aqua paints

Existing, exterior, treated, plastics (hard PVC)

- · remove unsound paint coats
- · clean / degrease thoroughly, and sand
- prime/ pre-finish partially or entirely with Ralston Aqua All-Primer
- · finish with Ralston Aqua paints

Existing, interior, treated, plastics (hard PVC)

- remove unsound paint coats
- · clean / degrease thoroughly, and sand

Product Data Sheet 5/6

Ralston Aqua All-Primer

- prime/ pre-finish partially or entirely with Ralston Aqua All-Primer
- · finish with Ralston Aqua paints

General remarks on paint systems and preparation

These remarks on paint application and maintenance are only general. The appropriate paint system to be applied will depend on both the substrate and the requirements to be met by the paintwork.

Regularly clean and repair any damage to paintwork

Regularly (preferably annually), clean the paintwork and repair any physical or other damage to the substrate or paintwork. This will have a beneficial effect on the condition of the painted object and its paint coating.

Adhesion between paint layers

Always sand or de-gloss between paint coating layers. This is essential for good adhesion of each new layer to the previous layer (with the exception of wall paints).

Regularly check the dew point

When working in lower temperatures, check the dew point frequently. Never apply new paint/coating onto a substrate with condensation (dew). If you do so, the adhesion and film formation will be degraded. Moisture also causes poor drying, and can ruin the gloss.

Repairs and compatibility with paint

Repairs to substrates, paintwork, connection joints/seams and glazing systems must be carried out with the appropriate products in accordance with the manufacturer's instructions. For wood repair, we prefer wood repair products based on epoxy or polyurethane and for sealing glazing joints to the Soudal Glaskit TS. The Soudal Acryrub CF2 can be used to seal joints and seams in interior wall paintwork. Prior to the commencement of the painting work, assess the mutual tolerance of the products to be applied.

Pretreatment, wooden substrates

Remove dirt and any weathered and/or degraded parts from wood and wood-based panels prior to application of the paint system in order to obtain a clean and sound substrate. By rounding off sharp edges, a longer protection of the substrate is obtained. Wood may contain up to 18% moisture during treatment.

For treatment, metal substrates

Remove rust and zinc salts thoroughly, so that an oxidation-free surface is obtained. Immediately after de-rusting / sanding, degrease and apply a primer layer. Degrease new hot-dip galvanised steel and aluminium before applying a primer coat and then blast lightly with a fine non-metallic abrasive using appropriate pressure.

Painting of synthetic substrates

There is

no suitable paint system for synthetic materials such as PE and PP.

The details in this product data sheet are correct at the time of printing. The information provided about this product is regularly updated, and amendments may therefore be made at any time without notice. Ralston Colour & Coatings B.V. expressly disclaims any and all liability related to damages resulting from errors or omissions in the information provided herein, except in the event of malicious intent or gross

Product Data Sheet 6/6 Ralston Aqua All-Primer

negligence.

For more information, please refer to the Safety Material Data Sheet or ask your paint supplier on www.ralstoncolour.com