

Product Data Sheet

Ralston Siloxan Mat

Excellent vapour permeable, weather resistant and easy to clean, mat facade paint based on siloxan modified acrylic dispersion.

- High water vapour permeability
- Water resistant and self cleaning (pearl effect)
- Anti algae and anti moss
- Good colour retention
- Excellent outdoor durability
- · Good hiding power









ralstoncolour.com /picto

PRODUCT

INTENDED USE	On isolated facades and exterior stony surfaces such as concrete, masonry, plaster and sheet material. For exterior use. If necessary, pre-treat with Ralston Siloxan Primer.
SITUATION	Exterior
PACKAGING	2.5 l, 10 l
COLOURS	All colours available via the Ralston AQ colour mixing system (the presence of special binders can cause a minor colour deviation)
GLOSS LEVEL	Perfectly matt, approx. 1 G.U. at 85 °
MAINTENANCE INTERVAL	Approx. 5 - 7 years
	Depending on location/ situation, surface to be treated, construction system, applied paint system and colour, mechanical impacting, etc
BINDER	Siloxane modified acrylate dispersion
PIGMENT	High quality pigments
SOLIDS CONTENT	Approx. 55 volume %
VISCOSITY AT 20 °C	Approx. 1,5 kg/dm3
DRYING TIME	Drying time (20 °C / 65 % R.H.): dust-free after approx.1 hr; recoatable after approx. 16 hr.
	Drying times are average values and provided as an indication only; actual drying time will depend on weather conditions, film thickness and choice of colour. Darker colours, applied in lower temperatures will take longer to dry than whites and lighter colours.
SCRUB RESISTANCE	Class 1, as per DIN EN 13 300 after 28 days.

Product Data Sheet 2/5 Ralston Siloxan Mat

COVERING CLASSClass 1 at economic use of 6 - 8 m2/l as per ISO 6504-3 and DIN EN 13
300WATER VAPOUR PERMEABILITY
(SD-VALUE)sd-value = 0,02 m, class V1: high (SD value < 0.14 m), as per EN
1062-1WATER VAPOUR DIFFUSION
RESISTANCEV = 807 g/(m2 x d), class V1: high (μ d value ≥ 150), as per EN 1062-1

NOTE: The properties and specifications can vary depending on the colour. The values stated are typical.

APPLICATION

APPLICATION BY SPRAY DATA	brush, roller, air-assisted airless		
	Pressure Orifice	air-assisted airless 12 - 15 MPa (120 - 150 bar) 0,018 - 0,021 inch	
DILUTION TOOLS/EQUIPMENT CLEANING	Dilution Ready to use Water.	max. 10 % water e. If necessary, dilute sparingly with water.	
APPLICATION TEMPERATURE / R.H. THEORETICAL COVERAGE	Min. 5 °C an 6 - 8 m2/l	bient and substrate temp., relative humidity max. 85 %.	

The application of a 'full' layer gives a long 'open time' which, combined with 'wet in wet' application, results in a finish that is free of 'lap marks'.

ENVIRONMENT AND CERTIFICATION

SAFETY INSTRUCTIONS	The user is subject to the national legislation regarding safety, health and environment. For more information and current data, see the latest version of the Safety Data Sheet.
EU LIMIT VALUE VOC	EU limit value for this product A/a: 30 g/l (2010). This product contains a maximum of 30 g/l VOCs.
BREEAM	 We herewith conform that our product can be used in compliance with BREEAM International New Construction. As per HEA 9, requirend evidence – completion phase: C 1.1 through to 1.8; in evidence of compliance, the following must be submitted: 1. VOS (Volatile Organic Substance) content as determined by product recipe. 2. Products grouped by category in accordance with European Decopaint Directive 2004/42/EC – Enclosure 2: Emission norm for paints, lacquers and clear finishes, phase 2. 3. EU limit value for this product A/a: 30 g/l (2010). This product contains a maximum of 30 g/l VOCs. and is compliant. We apply the above harmonization procedure as recommended by the Dutch Green Building Council.

Product Data Sheet 3/5 Ralston Siloxan Mat

BELGIAN EMISSION LABEL

The product complies with the limit values and other stipulations of the Royal Decree of 8 May 2014, which defines the threshold levels for emissions to the internal environment from construction products for designated, specific uses, as published in the Belgian Government Gazette of 8 August 2014.

FRENCH EMISSION LABEL



STORAGE AND USE PERIOD

STORAGE	Cool and above freezing point; do not allow product quality to deteriorate during storage.
SHELF LIFE	Use within 24 months of the date (charge no.) stated on the pack (figures 1 and 2 = year, figures 3 and 4 = week). Assumes unopened product. After opening the packaging, the effect of 'preservatives' in the paint may be reduced. In exceptional cases, this can give bacteria and moulds free rein from outside, which could spoil the product.

Product Data Sheet 4/5 Ralston Siloxan Mat

SYSTEM COMPOSITION - ADVICES

New, exterior, untreated, masonry

- · remove loose parts and any cement skin
- · repair where necessary
- pre-treat slightly powdery and/or absorbent substrates with Ralston Siloxan Primer
- treat entire surface with Ralston Siloxan Mat
- · treat entire surface with Ralston Siloxan Mat

Existing, exterior, treated, masonry

- remove unsound paint coats
- · repair where necessary
- pre-treat patches with Ralston Siloxan Primer
- treat patches or entire surface with Ralston Siloxan Mat
- · treat entire surface with Ralston Siloxan Mat

Existing, exterior, treated, masonry

- remove unsound paint coats
- repair where necessary
- · pre-treat patches with Ralston Siloxan Primer
- treat entire surface with Ralston Siloxan Mat

General remarks on paint systems and preparation

These remarks on paint application and maintenance are only general. The appropriate paint system to be applied will depend on both the substrate and the requirements to be met by the paintwork.

Regularly clean and repair any damage to paintwork

Regularly (preferably annually), clean the paintwork and repair any physical or other damage to the substrate or paintwork. This will have a beneficial effect on the condition of the painted object and its paint coating.

Adhesion between paint layers

Always sand or de-gloss between paint coating layers. This is essential for good adhesion of each new layer to the previous layer (with the exception of wall paints).

Regularly check the dew point

When working in lower temperatures, check the dew point frequently. Never apply new paint/coating onto a substrate with condensation (dew). If you do so, the adhesion and film formation will be degraded. Moisture also causes poor drying, and can ruin the gloss.

Repairs and compatibility with paint

Repairs to substrates, paintwork, connection joints/seams and glazing systems must be carried out with the appropriate products in accordance with the manufacturer's instructions. For wood repair, we prefer wood repair products based on epoxy or polyurethane and for sealing glazing joints to the Soudal Glaskit TS. The Soudal Acryrub CF2 can be used to seal joints and seams in interior wall paintwork. Prior to the commencement of the painting work, assess the mutual tolerance of the products to be applied.

Pretreatment of masonry

Stony substrates must be solid, load-bearing, sufficiently cured and clean before treatment. Remove any cement/laitance that may be present on cementitious substrates. Cement-bound substrates must be approx. 28 days old before applying a paint or coating. Plaster-bound substrates to be treated may contain max. 2% moisture and other stony substrates max. 4%.

Product Data Sheet 5/5 Ralston Siloxan Mat

The details in this product data sheet are correct at the time of printing. The information provided about this product is regularly updated, and amendments may therefore be made at any time without notice. Ralston Colour & Coatings B.V. expressly disclaims any and all liability related to damages resulting from errors or omissions in the information provided herein, except in the event of malicious intent or gross negligence.

For more information, please refer to the Safety Material Data Sheet or ask your paint supplier on www.ralstoncolour.com